

# Caprosyn™ suture

#### **PRODUCT INFORMATION**

Structure	monofilament
Suture Type	short-term absorbable
Composition	Polyglytone™ 6211 glycolide, caprolactone, trimethylene carbonate, and lactide
Coating	uncoated
Color	violet, undyed
Tensile Strength	10 days
Absorption Profile	56 days
Sizes	6-0 to 1
Indications	Caprosyn™ synthetic absorbable suture is indicated for use in general soft tissue approximation and/or ligation, but not for use in cardiovascular or neurological surgery, microsurgery, or ophthalmic surgery.
Contraindications	This suture, being absorbable, should not be used where extended approximation of tissue is required.
Sterilization Method	ethylene oxide
CE Marked	class III according to EU directive 93/42/EEC, annex II
Box Quantities	1, 2 or 3 dozen
Shelf Life	3 years
Temperature and Humidity Levels	Currently, the IFU for Medtronic Legacy Covidien SI Suture devices state to store at room temperature.
	In general, stability studies are performed with short term exposure to either 50 degrees (38 weeks) or 54.4 degrees (32 weeks) for accelerated aging testing purposes only. This condition is not intended for storage purposes.
	Real time testing is performed at 22 degrees +/- 10 degrees with uncontrolled humidity for the entirety of the device shelf-life.

### **SUTURE SUBSTANCES**

Phthalates Free	<b>~</b>
PVC Free	<b>~</b>
Bisfenol Free	<b>~</b>
Antimicrobial Substances Free	<b>~</b>
Latex Free	<b>~</b>
Triclosan Free*	<b>~</b>

<sup>\*</sup> Medtronic sutures are 100% triclosan free

### **ORDER INFORMATION**

Caprosyn™ codes can be identified with codes beginning with: C, SC, CC, XC, UC, GC

## **NEEDLE TECHNICAL INFORMATION**

For needle technical information, please refer to the **Needle Tech Sheet** 

